

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C04B 14/04, 14/10, C09C 1/02, 1/42		A1	(11) International Publication Number: WO 00/59841
			(43) International Publication Date: 12 October 2000 (12.10.00)
(21) International Application Number: PCT/US00/08485		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 31 March 2000 (31.03.00)			
(30) Priority Data: 60/127,379 1 April 1999 (01.04.99) US			
(71) Applicant (for all designated States except US): IMERYS PIGMENTS, INC. [US/US]; 100 Mansell Court, Suite 300, Roswell, GA 300769 (US).			
(72) Inventors; and (75) Inventors/Applicants (for US only): PRUETT, Robert, J. [US/US]; 113 Cambridge Drive N., Milledgeville, GA 31061 (US). YUAN, Jun [US/US]; 1646 Pine Valley Road, Milledgeville, GA 31061 (US). BROWN, Harry, Vincent, Jr. [US/US]; P.O. Box 5086, Sandersville, GA 31082 (US). CUMMINGS, David, O. [-/US]; Warthen, GA (US).			
(74) Agents: GARRETT, Arthur, S. et al.; Finnegan, Henderson, Farabow, Garrett & Dunner, L.L.P., 1300 I Street, N.W., Washington, DC 20005-3315 (US).		Published <i>With international search report.</i>	
(54) Title: KAOLIN CLAY PIGMENTS, THEIR PREPARATION AND USE			
(57) Abstract <p>A paper coating pigment manufactured from kaolin crude containing minor amounts of minerals. These pigments are used in lightweight coated and ultra-lightweight coated applications. The pigments comprise a phyllosilicate assemblage of minerals that yield a final pigment MgO content ranging between 0.04 to 0.3 weight percent and a K₂O content ranging between 0.12 and 0.8 weight percent based on the dry weight of the kaolin pigment. The mica in the pigment product is 1.0 % to 6.7 % by weight, and the smectite is 1.2 % to 9.1 % by weight of the kaolin. The presence of these weight percentages can be identified by a shape factor of 15 or greater. The viscous clay content of the feed to produce the pigment product is between 70 to 100 weight percent based on the dry weight of the kaolin clay. The pigment has a shape factor of ranging between 35 and 60 or greater, and greater than 80 % by weight of the particles are less than 2 microns, and greater than 12 % are less than 0.25 microns.</p>			

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY.

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

KAOLIN CLAY PIGMENTS, THEIR PREPARATION AND USE

1. Field of the Invention

The present invention relates to kaolin raw materials to produce novel kaolin clay pigments especially useful for coating lightweight and ultra-lightweight paper for rotogravure and offset printing.

More particularly, the invention relates to the use of kaolin crude having a desired amount of non-kaolin phyllosilicate clay minerals to produce mechanically delaminated kaolin coating pigments. These pigments possess a unique combination of desirable properties not available in other kaolin pigments. When used in certain coating compositions, these pigments yield superior gloss in coated and printed papers compared to other kaolin pigments.

2. Background of the Invention

Paper coating compositions are generally prepared by forming a fluid aqueous suspension of pigment material together with a hydrophilic adhesive and other optional ingredients.

Lightweight coated, or LWC, paper is generally coated to a weight of from about 5g.m^{-2} to about 13g.m^{-2} on each side, and the total grammage, or weight per unit area of the coated paper is generally in the

range of from about 49g.m^{-2} to about 65g.m^{-2} . LWC paper is generally used for printing magazines, catalogues and advertising or promotional material. The coated paper is required to meet certain standards of surface gloss and smoothness. For example, the paper is generally required to have a gloss value of at least about 32, and up to about 50, TAPPI units, and a Parker Print Surf value in the range of from about 0.5 to about 1.6_m.

Ultra lightweight coated, or ULWC, paper is sometimes otherwise known as light lightweight coated, or LLWC, paper and is used for catalogues and for advertising and promotional material sent through the mail to reduce mailing costs. The coating weight is generally in the range of from 5g.m^{-2} to 7g.m^{-2} per side. The grammage is generally in the range of from about 35g.m^{-2} to about 48g.m^{-2} .

A very important white inorganic pigment for use in preparing coating compositions for the manufacture of LWC and ULWC papers for rotogravure or offset printing is kaolin obtained from kaolin clay. Large deposits of kaolin clay exist in Devon and Cornwall, England and in the States of Georgia and South Carolina, United States of America. Important deposits also occur in Brazil, Australia, and in several other countries.

Kaolin clay, also referred to as china clay or hydrous kaolin, consists predominantly of mineral kaolinite ($\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4$), an hydrous aluminum silicate, together with small concentrations of various other minerals.

Some of these other minerals in kaolin, such as fine ferruginous or titaniferous impurities impart undesirable color to the clay. Many processing techniques are known to remove significant amounts of these impurity minerals.

Additional minerals in kaolin, which fall into a classification of silicates and referred to as phyllosilicates, comprise mica, smectite, vermiculite, hydrobiotite, mixed or layered illite-smectite or mixed layers of other clay minerals. These latter minerals are known to have higher water adsorption capability than kaolinite, and therefore, generally have an undesirable effect on the rheology of high solids kaolin-water suspensions. That is, these minerals cause the suspensions or slurries to thicken and become more viscous at high and low shear rates. The kaolin industry generally avoids mining clays with micaceous or smectitic minerals. Alternatively, the kaolin industry removes micaceous and smectitic minerals with processes, such as desliming, or the industry blends such clays with relatively pure kaolin ores to reduce the concentration of micaceous and smectitic minerals

to a level that does not affect clay-water suspension rheology. Examples of such beneficiation techniques include U.S. Patent Nos. 4,182,785; 4,334,985; 4,477,422; and 5,593,490.

Kaolinite is an hydrous aluminosilicate that exists in the form of clay-sized crystals in the shape of thin hexagonal plates or in booklets of platelets called "stacks". Kaolinite stacks may be subjected to a grinding action to easily separate or delaminate them into individual plates.

As long ago as 1939, Maloney disclosed in US-A-2158987 that the finish, or gloss, of a clay coated paper is greatly improved if the clay, before incorporation in the coating composition, is treated so that a large percentage, for example 80% by weight or more, of the clay particles have a size in the range of 0.1 μ m to 2 μ m. In order to increase the proportion of fine particles in the raw kaolin, the raw kaolin may, according to the disclosure in US-A-2158987 be subjected, before the centrifuging step, to a grinding or delamination operation in which a suspension containing from about 50% to about 75% by dry weight of kaolin and a dispersing agent is subjected to pebble milling. When the kaolin from the finer fraction is recovered, mixed with a suitable paper coating binder, and applied to the surface of a base paper, a coating of good gloss and color is obtained.

Various pigment products which are made using the principles described by Maloney in US-A-2158987 are commercially available and provide good gloss and smoothness in coated papers, especially for LWC and ULWC paper. For example, a pigment product available from Imerys Minerals Ltd., formerly ECC International Ltd., and recommended for gloss coatings of LWC consists of a refined English kaolin product having a particle size distribution, "psd", such that 89% by weight of the particles have an esd less than 2_m, 74% by weight of the particles have an esd less than 1_m and 25% by weight of the particles have an esd less than 0.25_m.

Generally, the commercially available pigment products used for gloss coatings of LWC and ULWC paper are delaminated kaolin products, that is, they are subjected to a grinding process in order to break the stacks into plates. For a typical delaminated product, a kaolin clay slurry may be subjected to magnetic separation, grinding or delaminating, classifying, leaching, and filtering. The kaolin may be spray dried or formed into slurry containing 65% solids. Delaminated kaolin pigments can be made into flowable slurry at 65% solids as compared to kaolin pigments at 70% solids. Solids concentration lower than 65% has been considered undesirable.

A kaolin product of high shape factor is considered to be more "platy" than a kaolin product of low shape factor. "Shape factor", as used herein, is a number that represents an average aspect ratio value (on a weight average basis) of particles, that is the ratio of particle diameter to particle thickness for a population of particles of varying size and shape as measured using the electrical conductivity method and apparatus described in GB-A-2240398/US-A-5128606/EP-A-0528078 and in US-A-5516617 and using the equations derived in these patent specifications. "Mean particle diameter" is defined as the diameter of a circle which has the same area as the largest face of the particle.

In the measurement method described in GB-A-2240398/US-A-5128606/EP-A-0528078 the electrical conductivity of a fully dispersed aqueous suspension of the particles under test is caused to flow through an elongated tube. Measurements of the electrical conductivity are taken between (a) a pair of electrodes separated from one another along the longitudinal axis of the tube, and (b) a pair of electrodes separated from one another across the transverse width of the tube, and using the difference between the two conductivity measurements the shape factor of the particulate material under test is determined.

The kaolin deposits in England are of primary kaolin, whilst those in the USA are of the primary and

secondary types. Kaolin was formed in geological times by the hydrothermal decomposition or by the weathering of the feldspar and mica components of granite and feldspathic metamorphic rocks, and primary kaolin is that which is obtained directly from the crystalline rock matrix in which it was originally formed. On the other hand, secondary kaolin, also known as sedimentary kaolin, has been washed out of the original primary kaolin matrix in geological times and has been deposited in an area remote from the site in which it was originally formed. Secondary kaolin deposits tend to have a higher proportion of fine particles, such as those having an esd smaller than 2 μ m, because the kaolin has undergone a certain amount of natural grinding and sorting during the course of its transport from its site of origin to its site of final deposition.

Kaolin products generally are produced from a kaolin crude which is mined from the zones or strata in the primary and secondary clay deposits that contain the highest concentration of kaolinite and lowest concentration of other clay-sized 2:1 phyllosilicate minerals. In the past, the kaolin clay mineral producing industries, particularly in Georgia, have avoided using lower quality crude ores that contain elevated levels of minor minerals, such as the phyllosilicates, including mica, smectite, vermiculite,

hydrobiotite, mixed or layered illite-smectite or mixed layers of other clay minerals. These minor minerals had been considered to be impurities which made the kaolin crude undesirable for standard wet-processed and delaminated products because of the poor clay-water viscosity.

Unexpectedly, the inventors have discovered that the kaolin crudes containing certain amounts of non-kaolinite phyllosilicates possess greater aspect ratio, that is, the kaolin crudes are more "platy", than conventionally used kaolin crude clays. By using these particular crude clays, the inventors have found a method to make novel products which possess significantly higher aspect ratio, greater amounts of non-kaolinite minerals, and lower, flowable solids concentration of kaolin-water suspensions compared to conventional kaolin pigments. These novel pigments with these special properties have been found to yield glossing characteristics for LWC and ULWC coated and printed papers that are far superior to those from other pigments.

SUMMARY OF THE INVENTION

A first aspect of the invention provides a kaolin clay pigment comprising a phyllosilicate assemblage of minerals, such as smectite and mica. Preferably, the

kaolin crude ore used to produce the clay pigment comprises smectitic clays, preferably smectite, ranging from 0.9% to about 15.0% by weight, more preferably, from about 1.2% to about 7.6% by weight, and most preferably, from about 1.5% to about 4.5% by weight based on the kaolin clay in the crude. Preferably, the percentage of micaceous clays, more preferably mica, in the kaolin crude will range from about 0.9% to about 26.0% by weight, more preferably, from about 1.7% to about 17.0% by weight, and more preferably, from about 4.2% to about 8.6% by weight, based on the dry weight of kaolin clay. The amount of smectitic clays, preferably smectite, appearing in the kaolin clay pigment preferably will range from about 1.2% to about 9.1%, more preferably, from about 1.5% to about 6.0%, and most preferably from about 1.8% to about 3.0% by weight based on the dry weight of the kaolin. The amount of micaceous clays, preferably mica, in the kaolin pigment product preferably will range from about 1.0% to about 6.7%, more preferably, from about 1.2% to about 3.4%, and most preferably, from about 1.3% to about 2.1% by weight, based on the dry weight of the kaolin in the pigment product.

Generally, the kaolin crude contains a desirable amount of minerals, such as the phyllosilicates listed herein above. These phyllosilicates, preferably, yield potassium oxides and magnesium oxides where the major

oxide concentration of potassium preferably is between about 0.1 to about 3.0% by weight, more preferably, from about 0.2% to about 2.0% by weight, and most preferably, between from about 0.5% to about 1.0% by weight, based on the dry weight of the crude kaolin clay. The major oxide concentration of magnesium in the crude preferably is between about 0.03% to about 0.50% by weight, more preferably, from about 0.04% to about 0.25% by weight, and most preferably, from about 0.05% to about 0.15% by weight, based on the dry weight of the kaolin crude. Such crude may be naturally platy clay, such as those in Middle Georgia, U.S.A. with a shape factor ranging between 15 to 30, or higher.

Preferably, the kaolin pigment product comprises phyllosilicates, such as smectite and/or mica, where the major oxide concentration of potassium (K_2O) preferably, ranges between from about 0.12% to about 0.8% by weight, more preferably, from about 0.14% to about 0.9% by weight, and most preferably, from about 0.15% to about 0.25% by weight, based on the dry weight of the kaolin pigment. The major oxide concentration of magnesium (MgO) in the pigment product preferably ranges from between about 0.04% to about 0.3% by weight, more preferably, from about 0.05% to about 0.2% by weight, and most preferably, from about 0.06% to about 0.1% by weight, based on the dry weight of the kaolin pigment.

The particle size distribution of the kaolin clay pigment may be such that preferably, 80 to 95% by weight of the particles have an equivalent spherical diameter (esd) less than 2 microns.

A method for producing a kaolin pigment product comprises the steps of:

(a) mixing a raw kaolin clay crude, comprising at least about 0.9% by weight mica and about 0.9% by weight smectite, based on the dry weight of the crude, where the K_2O content ranges between about 0.10% by weight to about 3.0% by weight and the MgO content ranges between about 0.03% by weight to about 0.50% by weight, based on the dry weight of the kaolin clay crude, with water to form an aqueous suspension containing from 20% to 70% of kaolin on a dry weight basis;

(b) subjecting the suspension produced by step (a) to attrition grinding using a particulate grinding medium for a time sufficient to delaminate the majority of stock of kaolin clay crude with a shape factor from about 35 to greater than 60;

(c) separating the suspension of ground kaolin clay from the particulate grinding medium;

(d) subjecting the suspension of step (c) to a particle size classification step; and

(e) dewatering the suspension of ground kaolin clay classified in step (d) to recover a pigment

product therefrom, said pigment product comprising from about 1.0% to about 6.7% by weight mica and about 1.2% to about 9.1% by weight smectite based on the dry weight of the kaolin clay in the pigment product, where the K_2O content of the pigment product ranges between about 0.12% by weight to about 0.8% by weight and the MgO content of the pigment product ranges from between about 0.04% by weight and about 0.3% by weight, based on the dry weight of the kaolin clay in the pigment product, and the particle size distribution of the final pigment product is such that about 80% to 95% by weight of the particles have an esd less than 2 microns.

In step (e) and as a result of step (d), the kaolin clay particles may have a particle size distribution such that 80% to 95% by weight of the particles have an esd less than 2 microns and at least 12%, preferably 20% to 40%, and most preferably 25% to 35%, by weight of the particles have an esd less than 0.25 microns.

Since the pigment products of the invention are typically 80% to 95% by weight finer than 2 micrometers, and the surface area may be greater than $12m^2/g$, and preferably between $15m^2/g$ to $20m^2/g$ when measured by the BET method, they may be classified as No. 1 kaolin clay pigments. In step (a) the shape factor of the naturally platy clay prior to any

delamination or grinding thereof is at least 15 and, preferably, is greater than 25, and most preferably is greater than 30. As a result of the shape factor produced in step (b) above ranging from about 35 to greater than 60, the kaolin clay particles finer than 2 micrometers are extremely platy. The viscous clay content ranges between about 70 percent to about 100 percent by weight based on the dry weight of the kaolin clay of the processed feed.

The pigment product of the invention has been shown to give greater improvement in sheet brightness, opacity, and gloss as compared to standard products in starch containing binder systems. Pigments of the invention are particularly useful in coating compositions for coating lightweight (LWC) and ultra-lightweight (ULWC) printed paper.

DETAILED DESCRIPTION OF THE INVENTION

The novel hydrous kaolin pigments of the invention are adapted for coating LWC and ULWC paper adapted to be printed by offset and rotogravure and comprise a major amount of platy kaolin particles where the platiness of the kaolin particles is defined in terms of a "high" shape factor, that is, the average shape factor of the particles of the pigment is at least 35, preferably 55, and desirably greater than 60.

The pigment product according to a first aspect of the present invention may be obtained by treating a raw particulate hydrous naturally platy kaolin mineral obtained from selected zones of the sedimentary kaolin, such as that which occurs in Georgia, USA. Preferably, this crude at least has minor amounts of micaceous and/or smectitic minerals.

Preferably, the kaolin crude ore comprises smectite ranging from about 0.9% to about 15.0% by weight, more preferably, from about 1.2% to about 7.6% by weight, and most preferably, from about 1.5% to about 4.5% by weight based on the kaolin clay in the crude. Preferably, the percentage of mica in the kaolin crude will range from about 0.9% to about 26.0% by weight, more preferably, from about 1.7% to about 17.0% by weight, and more preferably, from about 4.2% to about 8.6% by weight, based on the dry weight of crude kaolin clay. The amount of smectite appearing in the kaolin clay pigment, preferably, will range from about 1.2% to about 9.1%, more preferably, from about 1.5% to about 6.0%, and most preferably, from about 1.8% to about 3.0% by weight, based on the dry weight of the kaolin.

The amount of mica in the kaolin pigment product, preferably, will range from about 1.0% to about 6.7%, more preferably, from about 1.2% to about 3.4%, and most preferably, from about 1.3% to about 2.1% by

weight, based on the dry weight of the kaolin in the pigment product.

Generally, the kaolin crude contains a desirable amount of minerals, such as the phyllosilicates listed herein above. These phyllosilicates, preferably, yield bulk K_2O content between about 0.1 to about 3.0% by weight, more preferably, from about 0.2% to about 2.0% by weight, and most preferably, between from about 0.5% to about 1.0% by weight, based on the dry weight of the crude kaolin clay. The MgO content in the crude preferably is between about 0.03% to about 0.50% by weight, more preferably, from about 0.04% to about 0.25% by weight, and most preferably, from about 0.05% to about 0.15% by weight, based on the dry weight of the kaolin crude. Such crude may be naturally platy clay, such as those in Middle Georgia, U.S.A. with a shape factor ranging between 15 to 30, or higher.

Preferably, the kaolin pigment product comprises phyllosilicates, such as smectite and/or mica, where the pigment K_2O content ranges from about 0.12% to about 0.8% by weight, more preferably, from about 0.14% to about 0.9% by weight, and most preferably, from about 0.15% to about 0.25% by weight, based on the dry weight of the kaolin pigment. The MgO in the pigment product ranges from between about 0.04% to about 0.3% by weight, more preferably, from about 0.05% to about 0.2% by weight, and most preferably, from about 0.06%

to about 0.1% by weight, based on the dry weight of the kaolin pigment.

The particle size distribution of the kaolin clay pigment may be such that 80% to 95%, preferably 85% to 92%, and most preferably, 88% to 92% by weight have an equivalent spherical diameter (esd) less than 2 microns, and at least 12, preferably from 20 to 40%, and most preferably from 25% to 35% by weight have an equivalent spherical diameter less 0.25 micrometers or microns.

The kaolin pigments of the invention may have the following further characteristics:

Bulk Chemistry of Kaolin Pigment Product

Smectite, in the form of calcium montmorillonite typically found in Georgia kaolin generally has the formula $\text{Ca}_{0.15}(\text{Mg}_{0.3}\text{Al}_{1.7})\text{SiO}_4(\text{OH})_2$. Micas found in Georgia kaolin can be represented by the formula $\text{K}(\text{Al}_{1.806}\text{Fe}_{0.194})\text{Al Si}_3\text{O}_{10}(\text{OH})_2$. Weathered micas, illite and the illite layers in mixed layered illite-smectite may contain 70% or less of the potassium level, on a molar basis, shown in the formula for a typical mica from Georgia kaolin. Kaolin pigment products having minor amounts of minerals contain potassium and magnesium in their crystal structures. The proportions of these elements in the minor clay minerals and their total concentration after processing yields pigments having

K₂O content ranging between about 0.12 to about 0.8% by weight and MgO content ranging between about 0.04% and 3.0% by weight, based on the dry weight of the kaolin pigment.

Platy Content

Viscous clay content of the feed to produce pigment products is between 70 to about 100 weight percent, based on the dry weight of the kaolin clay.

Surface Area

BET surface area greater than 12m²/g, preferably ranging between 15m²/g to 20m²/g.

Solids Content

The solids content may be at least 50% by weight, preferably ranging from 61.0 to about 64.0% by weight of kaolin clay particles in dry weight form.

The starting crude ore useful in the invention generally is viscous, sedimentary kaolin containing micas, mixed-layered clay minerals, smectites, and vermiculites or hydrous micas. A "viscous" kaolin clay can be defined as being a clay that will not make-down into a clay-water slurry at greater than or equal to 70% solids. Such crude may have a shape factor equal

to or greater than 15, preferably, equal to or greater than 25.

One investigation performed by the inventors found several sedimentary kaolin localities in Middle Georgia that contain platy clay with some localities having marginally platy clay. These deposits can be classified into six different mineralogical groups which are summarized in Table 1 below.

TABLE 1

Platy-Clay Group	Mineral Content			
	Kaolinite	Illite	Smectite	I/S
I	Nearly Pure			
II	Major			Trace
III	Major	Trace Or Minor		
IV	Major		Trace	
V	Major	Trace	Trace	
VI	Trace	Trace	Major	

The kaolin resources used in the invention pertain to Groups II, III, IV and V of Table 1, which in addition to containing mostly kaolinite, have minor amounts of illite, smectite, or illite-smectite (I/S).

The presence of the different minor minerals, such as phyllosilicates, including smectite, illite, and illite-smectite, in the kaolin crudes is detected by X-Ray powder diffraction analysis. These minerals differ from kaolinite in that these minerals are generally 2:1 sheet silicates having interlayer cations.

Mica, illite, and illite layers in mixed-layered clay minerals contain potassium as an interlayer cation in their structure. The potassium in the interlayer site acts to compensate for a negative charge imbalance

caused by the aluminum substitution for silicon in the tetrahedral layer of these minerals. The inventors have found that the potassium level is a precise indicator of the concentration of these minerals in Georgia sedimentary kaolins because no other potassium-bearing minerals, such as potassium feldspar, are present in significant amounts.

Smectite in the Georgia sedimentary clays is generally a calcium montmorillonite, which, in turn, has magnesium in its octahedral layer. Mica, illite, and illite-smectite can have minor levels of magnesium in their crystal structures, but the inventors have found that the magnesium concentration in Georgia sedimentary kaolins is a relatively precise measurement of smectite content because no other magnesium-bearing minerals with significant levels of magnesium in their structures are present in significant amounts.

Preferably, the kaolin clay crude used in the invention is comprised of about 0.10% to about 3.0% by weight of potassium oxide and about 0.03% to about 0.50% by weight of magnesium oxide. As stated hereinabove, these elements are structural components of minor phyllosilicate phases in the kaolin, and the phyllosilicates are mixed in with the kaolinite. The result is a mixture of platy kaolinite particles and platy non-kaolinite phyllosilicate particles that may

have a higher average diameter to thickness ratio than the kaolinite particles.

X-Ray Fluorescence (XRF) analysis can be a more sensitive method to X-Ray powder diffraction analysis for determining the minor clay mineral content in Georgia sedimentary clays. XRF is an instrument that determines the weight percentage of potassium oxide (K_2O) and magnesium oxide (MgO) in kaolin materials. The K_2O and MgO content of kaolin materials are then divided by the K_2O or MgO content of the pure mica or smectite phase to determine mica and smectite content of the kaolin material.

As stated above, the starting crude ore useful in the invention generally is viscous, sedimentary kaolin containing micas, mixed-layered clay minerals, smectites, and vermiculites or hydrous micas. Although the starting sedimentary crude ore discussed in the examples is located in Georgia, the present invention is also directed to sedimentary crude ores having such characteristics located elsewhere in the world. Such crude ores may be found elsewhere in North America, South America, Europe, and Asia. Such countries include, but are not limited to Canada, Mexico, U.S.A., Brazil, Argentina, Finland, China, and Australia.

One method of determining whether a kaolin is from a primary or secondary deposit is by measuring the titanium dioxide (TiO_2) level of the kaolin. For

example, the titanium dioxide amount, by percent weight of the kaolin measured on a dry basis, of Georgia sedimentary crudes is between 1% and 3.5%. Such crudes after general processing (where limited titanium dioxide removal is undertaken) often have titanium dioxide amounts of between 1.2% and 1.9%. Such crudes after targeted processing to remove titanium dioxide (such as by selective flocculation, flotation, or magnetic separation methods) often have titanium dioxide levels between 0.1 and 0.7%, and generally have levels at or above 0.3% due to the substantial cost of such targeted titanium dioxide removal processes. In contrast, the titanium dioxide amount of primary deposits located in Cornwall, England, is generally between 0.02 and 0.4%. After general processing, such kaolin generally only contains 0.01 to 0.2% titanium dioxide. Generally, primary kaolin deposits do not undergo targeted titanium dioxide removal processes as they contain such low levels of titanium that may be substituted for primary elements within silicate minerals or occur in low levels in accessory minerals such as sphene, $\text{CaTi}[\text{SiO}_4](\text{O}, \text{OH}, \text{F})$, andradite, $\text{Ca}_3(\text{Fe}, \text{Ti})_2\text{Si}_3\text{O}_{12}$, Ilmenite, FeTiO_3 , or perovskite, CaTiO_3 , rather than occurring as titania minerals such as anatase, with lesser amounts of rutile or brookite, as typical for most commercial sedimentary kaolins. The above percentages are for titanium dioxide, in weight

percent, as measured in bulk sample on a dry basis using an x-ray fluorescence spectrometer.

The kaolin pigment of the invention when used in a coating formulation yields coated paper, which exhibits "good" sheet gloss and "good" print gloss.

The pigment product of the invention preferably has a particle size distribution "psd" such that at about 80% to 95% by weight of the particles have an esd smaller than 2_μm and about 20% to 40%, preferably 25% to 35%, by weight of the particles have an esd smaller than 0.25_μm, and a shape factor of at least 35, preferably, greater than 60.

As will be appreciated by those skilled in the art, the psd of a particulate product such as the pigment product according to the present invention may be determined by measuring the speeds at which dispersed particles of the particulate product under test sediment through a standard dilute aqueous suspension using a SEDIGRAPH™ instrument, such as SEDIGRAPH 5100, obtained from Micromeritics Corporation, USA. The size of a given particle is expressed in terms of the diameter of a sphere of equivalent diameter, which sediments through the suspension is expressed as the equivalent spherical diameter or esd, the parameter as referred to above. The SEDIGRAPH instrument measures and graphically

records the percentage by weight of particles having esd less than a certain esd value versus esd.

The particles in these crudes, for example, the particles may be very fine booklets or fine individual particles. Attrition grinding preferably is applied to the crude particles prior to a classification step in order to increase the number of fine individual platelets. That is, the shape factor may be increased to from about 20 to about 60 or greater.

The method of a second aspect of the invention comprises:

(a) mixing a raw kaolin clay crude, comprising about 0.9 to 26.0% by weight mica and about 0.9% to about 15.0% by weight smectite comprising K_2O content between about 0.10% to about 3.0% by weight and MgO content between about 0.03% to about 0.50% by weight, based on the weight of the kaolin clay, with water to form an aqueous suspension containing from 20% to 70% of kaolin on a dry weight basis;

(b) subjecting the suspension produced by step (a) to attrition grinding using a particulate grinding medium for a time sufficient to delaminate the majority of stacks of kaolin crude to an average shape factor value to the kaolin clay particles ranging between from about 35 to about 65;

(c) separating the suspension of ground kaolin clay from the particulate grinding medium; and

(d) subjecting the suspension of step (c) to a particle size classification step;

(e) dewatering the suspension to a ground kaolin clay classified in step (d) to recover a pigment product therefrom, said product comprising a phyllosilicate assemblage of minerals that yield a K_2O content between about 0.12% to about 0.8% by weight and MgO content between about 0.04% to about 0.30% by weight, based on the dry weight of the kaolin pigment.

Beneficiation steps to improve clay brightness, such as magnetic separation, ozone, reduced-acid leaching, flotation, or selective flocculation, may be performed on the clay suspension or slurry prior to or after the attrition grinding step of step (b).

Typically, in step (a) the crude is initially crushed and then mechanically worked, such as by blunging in water, preferably containing clay dispersant, such as, for example, one or more inorganic or organic agents well known in the art. In the invention, it is preferred to use a mixture of sodium hexametaphosphate and soda ash. Generally, the solids of the blunged clay are in the range of 20% to 65%. The blunged clay slurry may be degrittied by passing the slurry through dreg boxes and a +325 mesh (U.S. standard) screen to remove coarse (grit) particles larger than 45 microns. The slurry may then be

subjected to a high intensity magnetic separator to remove the iron-bearing minerals from the clay.

From the magnetic separator, and as described in step (b), the clay slurry is subjected to an attrition grinding step using a particulate grinding medium for a time sufficient to dissipate in the suspension enough energy to impart an average shape factor value to the particles ranging from about 35 to 60 or greater. The amount of energy may range from 20 to 100kWh, preferably, about 25 to 50kWh energy per ton of kaolin.

The attrition grinding mill is equipped with a stirrer, which is capable of being rotated at a speed such that a vortex is formed in the suspension in the mill during grinding. The particulate grinding medium preferably has a specific gravity of 2 or more, and advantageously comprises grains of silica sand or similar media, the grains generally having diameters not larger than about 2 mm and not smaller than about 0.25 mm

As recited in step (c), the slurry of ground kaolin clay is separated from the grinding medium in a known manner, such as by passing the suspension through a sieve of appropriate aperture size, for example, a sieve having normal aperture size in the range of from about 0.1 mm to about 0.25 mm.

After the separation step (c), the clay slurry is passed through a Bird centrifuge for a classification

step. In step (d), the clay is classified to a particle size distribution such that 80% to 95% by weight, preferably 85% to 92% by weight of the particles have an esd less than 2 microns and between 20% to 40%, preferably between 25% to 35% by weight of the particles have an esd less than 0.25 microns.

In step (e), the suspension of ground kaolin may be dewatered in one of the ways well known in the art, such as filtration, centrifugation, evaporation and the like. Between steps (d) and (e), the suspension may be subjected to a leaching process to remove iron oxides and to change the shade of the clay. The leaching step may involve filtration to separate the dissolved iron and salts from the clay products.

After the dewatering step (e), the solids content of the slurry may be about 50% by weight, preferably ranging from 61% to at least 64.0% by weight of kaolin clay particles in dry weight form. This solids content represents "good" rheology.

The viscous clay crude component of the feed to produce the pigment product of the invention may range from about 70% by weight to about 100% by weight, based on the dry weight of the kaolin clay. If the particle size distribution of the kaolin crude particles is 75% by weight less than 2 microns (coarse clay), then a viscous clay could be defined as having a 15+ shape factor in bulk, and the < 2 micron particles would have

a shape factor of 25 or greater. The crude viscosity measured by Brookfield would be about 1500cps or greater at 70% solids. If the particle size distribution of the kaolin crude particles is 75% greater than 2 microns (fine clay), then the viscous clay could be defined as having a shape factor 25 or greater, and a crude Brookfield viscosity of 1500cps or greater at 70% solids. Viscous clay can occur as separate clay beds from non-viscous clays or it could occur as bands within individual non-viscous clay beds.

The invention uses whole or nearly whole, from about 70% to 100%, poor rheology (viscous) crude which generally is not mined or which is blended at a level below 50% solids with good rheology crudes. It has been found by the inventors that these poor quality crudes can be used to produce a very high value product for the paper industry.

According to the present invention in a third aspect there is provided a coating composition for use in producing gloss coatings on paper and other substrates which composition comprises an aqueous suspension of a particulate pigment together with a hydrophilic adhesive or binder, wherein the particulate pigment comprises the pigment product according to the first aspect of the invention.

The pigment product according to the first aspect of the present invention may be used in paper coating as follows.

The clay content of the pigment in a paper coating composition according to the third aspect of the invention may be greater than 60% by weight, preferably at least 70%, preferably as high as possible but still giving a suitably fluid composition which may be used in coating. The composition may include a dispersing agent, generally up to 2% by weight of a polyelectrolyte based on the dry weight of pigment present. For example, polyacrylates and copolymers containing polyacrylate units are well known as suitable polyelectrolytes.

The pigment product according to the first aspect of the invention may be used as the sole pigment in the paper coating composition according to the third aspect, or it may be used in conjunction with one or more other known pigments, such as for example, (commercially available) kaolin, calcined kaolin, natural or precipitated calcium carbonate, titanium dioxide, calcium sulphate, satin white, talc and so called "plastic pigment". When a mixture of pigments is used, the pigment product according to the first aspect of the invention is preferably present in the mixture in an amount of at least 80% of the total dry weight of the mixed pigments.

The binder of the composition according to the third aspect may conveniently comprise an adhesive derived from natural starch obtained from a known plant source, for example, wheat, maize, potato or tapioca although it is not essential to use starch as a binder ingredient. Other binders, which may be used with or without starch, are mentioned later.

Where starch is employed as a binder ingredient, the starch may be unmodified or raw starch, or it may be modified by one or more chemical treatments known in the art. The starch may, for example, be oxidized to convert some of its $-CH_2OH$ groups to $-COOH$ groups. In some cases the starch may have a small proportion of acetyl, $-COCH_3$, groups. Alternatively, the starch may be chemically treated to render it cationic or amphoteric (with both cationic and anionic charges). The starch may also be converted to starch ether, or hydroxyalkylated starch by replacing some $-OH$ groups with, for example, $-O.CH_2.CH_2OH$ groups, $-O.CH_2.CH_3$ groups or $-O.CH_2.CH_2.CH_2OH$ groups. A further class of chemically treated starches, which may be used, is that known as the starch phosphates. Alternatively, the raw starch may be hydrolyzed by means of a dilute acid or an enzyme to produce a gum of the dextrin type. The amount of the starch binder used in the composition according to the third aspect is preferably from 4% to 25% by weight, based on the dry weight of pigment. The

starch binder may be used in conjunction with one or more other binders, for example synthetic binders of the latex or polyvinyl acetate or polyvinyl alcohol type. When the starch binder is used in conjunction with another binder, such as a synthetic binder, the amount of the starch binder is preferably from 2% to 20% by weight, and the amount of the synthetic binder from 2% to 12% by weight, both based on the weight of dry pigment. Preferably, at least 50% by weight of the binder mixture comprises modified or unmodified starch.

According to the present invention in a fourth aspect there is provided a method of use of the coating composition according to the third aspect which comprises applying the composition to coat a sheet of paper and calendering the paper to form a gloss coating thereon. Preferably, the gloss coating is formed on both sides of the paper.

Calendering is a well known process in which paper smoothness and gloss is improved and bulk is reduced by passing a coated paper sheet between calender nips or rollers one or more times. Usually, elastomer coated rolls are employed to give pressing of high solids compositions. An elevated temperature may be applied.

Five or more passes through the nips may be applied.

The paper after coating and calendering in the method according to the fourth aspect may have a total weight per unit area in the range 30g.m^{-2} to 70g.m^{-2} ,

especially 49g.m^{-2} to 65g.m^{-2} or 35g.m^{-2} to 48g.m^{-2} . The final coating preferably has a weight per unit area preferably from 3g.m^{-2} to 20g.m^{-2} , especially from 5g.m^{-2} to 13g.m^{-2} . Such a coating may be applied to both sides of the paper. Thus, the coated paper may be LWC or ULWC paper. The paper gloss may be greater than 45 TAPPI units and the Parker Print Surf value at a pressure of 1mPa of each paper coating may be less than 1m .

The gloss of a coated paper surface may be measured by means of a test laid down in TAPPI Standard No 480 ts-65. The intensity of light reflected at an angle from the surface of the paper is measured and compared with a standard of known gloss value. The beams of incident and reflected light are both at an angle of 75° to the normal to the paper surface. The results are expressed in TAPPI gloss units.

The Parker Print Surf test provides a measure of the smoothness of a paper surface, and comprises measuring the rate at which air under pressure leaks from a sample of the coated paper which is clamped, under a known standard force, between an upper plate which incorporates an outlet for the compressed air and a lower plate, the upper surface of which is covered with a sheet of either a soft or a hard reference supporting material according to the nature of the paper under test. From the rate of escape of the air,

a root mean cube gap in μ m between the paper surface and the reference material is calculated. A smaller value of this gap represents a higher degree of smoothness of the surface of the paper under test.

The pigment of the invention has been shown to give greater improvement in sheet brightness, opacity, and gloss as compared to standard products in starch containing binder systems. However, an improvement may also be obtained where other known starch-free binders are employed (with or without starch present). In each case the adhesive or binder may form from 4% to 30%, preferably from 8% to 20%, and most preferably from 8% to 15% by weight of the solids content of the composition. The amount employed will depend upon the composition and the type of adhesive, which may itself incorporate one or more ingredients. For example, hydrophilic adhesives used in the art may incorporate one or more of the following adhesive or binder ingredients for use in the following stated amounts:

(a) latex: levels range from 4% by weight to 20% by weight. The latex may comprise for example a styrene butadiene, acrylic latex, vinyl acetate latex, or styrene acrylic copolymers.

(b) other binders: levels again range from generally 4% by weight to 20% by weight. Examples of other binders include casein, polyvinyl alcohol and polyvinyl acetate.

Additives in various known classes may, depending upon the type of coating and material to be coated, be included in the coating composition according to the third aspect of the present invention. Examples of such classes of optional additive are as follows:

(a) cross linkers: generally in levels of up to 5% by weight; for example glyoxals, melamine formaldehyde resins, ammonium zirconium carbonates.

(b) water retention aids: generally up to 2% by weight, for example sodium carboxymethyl cellulose, hydroxyethyl cellulose, PVA (polyvinyl acetate), starches, proteins, polyacrylates, gums, alginates, polyacrylamide bentonite and other commercially available products sold for such applications.

(c) viscosity modifiers or thickeners: generally in levels up to 2% by weight; for example polyacrylates, emulsion copolymers, dicyanamide, triols, polyoxyethylene ether, urea, sulphated castor oil, polyvinyl pyrrolidone, montmorillonite, CMC (carboxymethyl celluloses), sodium alginate, xanthan gum, sodium silicate, acrylic acid copolymers, HMC (hydroxymethyl celluloses), HEC (hydroxyethyl celluloses) and others.

(d) lubricity/calendering aids: generally in levels up to 2% by weight, for example calcium stearate, ammonium stearate, zinc stearate, wax emulsions, waxes, alkyl ketene dimer, glycols.

(e) **dispersants:** generally in levels up to 2 per cent by weight, for example polyelectrolytes such as polyacrylates and copolymers containing polyacrylate species, especially polyacrylate salts (such as sodium and aluminium optionally with a group II metal salt), sodium hexametaphosphates, non-ionic polyol, polyphosphoric acid, condensed sodium phosphate, non-ionic surfactants, alkanolamine and other reagents commonly used for this function.

(f) **antifoamers/defoamers:** generally in levels up to 1% by weight, for example blends of surfactants, tributyl phosphate, fatty polyoxyethylene esters plus fatty alcohols, fatty acid soaps, silicone emulsions and other silicone containing compositions, waxes and inorganic particulates in mineral oil, blends of emulsified hydrocarbons and other compounds sold commercially to carry out this function.

(g) **dry or wet pick improvement additives:** generally in levels up to 2% by weight, for example melamine resin, polyethylene emulsions, urea formaldehyde, melamine formaldehyde, polyamide, calcium stearate, styrene maleic anhydride and others.

(h) **dry or wet rub improvement and abrasion resistance additives:** generally in levels up to 2% by weight, for example glyoxal based resins, oxidized polyethylenes, melamine resins, urea formaldehyde, melamine

formaldehyde, polyethylene wax, calcium stearate and others.

(i) **gloss-ink hold-out additives:** generally in levels up to 2% by weight, for example oxidized polyethylenes, polyethylene emulsions, waxes, casein, guar gum, CMC, HMC, calcium stearate, ammonium stearate, sodium alginate and others.

(j) **optical brightening agents (OBA) and fluorescent whitening agents (FWA):** generally in levels up to 1% by weight, for example stilbene derivatives.

(k) **dyes:** generally in levels up to 0.5% by weight.

(l) **biocides/spoilage control agents:** generally in levels up to 1% by weight, for example metaborate, sodium dodecylbenene sulphonate, thiocyanate, organosulphur, sodium benzonate and other compounds sold commercially for this function, such as the range of biocide polymers sold by Calgon Corporation.

(m) **leveling and evening aids:** generally in levels up to 2% by weight, for example non-ionic polyol, polyethylene emulsions, fatty acid, esters and alcohol derivatives, alcohol/ethylene oxide, sodium CMC, HEC, alginates, calcium stearate and other compounds sold commercially for this function.

(n) **grease and oil resistance additives:** generally in levels up to 2% by weight of additives such as oxidized polyethylenes, latex, SMA (styrene maleic anhydride), polyamide, waxes, alginate, protein, CMC, HMC.

(o) **water resistance additives:** generally in levels up to 2% by weight, of additives such as oxidized polyethylenes, ketone resin, anionic latex, polyurethane, SMA, glyoxal, melamine resin, urea formaldehyde, melamine formaldehyde, polyamide, glyoxals, stearates and other materials commercially available for this function.

(p) **insolubiliser:** generally in levels up to 2% by weight.

For all of the above additives, the percentages by weight quoted are based on the dry weight of pigment (100%) present in the composition. Where the additive is present in a minimum amount the minimum amount may be 0.01% by weight based on the dry weight of pigment.

The method according to the fourth aspect of the present invention may be carried out in a known way which will depend upon the material to be coated, the coating composition to be applied and other factors as determined by the operator, such as speed and ease of runnability and use of a conventional coating machine.

Methods of coating paper and other sheet materials are widely published and well known. For example, there is a review of such methods published in Pulp and Paper International, May 1994, page 18 et seq. Sheets may be coated on the sheet-forming machine. This coating may be "on-machine", or "off-machine" on a coater or coating machine. Use of high solids

All known methods of coating according a fourth aspect of the present invention require (i) a means of applying the coating composition to the material to be coated, viz. an applicator; and (ii) a means for ensuring that a correct level of coating composition is applied, viz. a metering device. When an excess of coating composition is applied to the applicator, the metering device is downstream of it. Alternatively, the correct amount of coating composition may be applied to the applicator by the metering device, for example, a film press. At the points of coating application and metering, the paper web support ranges from a backing roll, such as via one or two applicators, to nothing (just tension). The time the coating is in contact with the paper before the excess is finally removed is the dwell time - and this may be short, long or variable.

38

formulation and optionally less pigment in the coating composition. A coater that is applying a double coating, such as a coating on each side of the paper, will have two or four coating heads, depending on the number of sides coated by each head. Most coating heads coat only one side at a time, but some roll coaters (such as a film press, a gate roll, and a size press) coat both sides in one pass.

Examples of known coaters which may be employed in step (b) include air knife coaters, blade coaters, rod coaters, bar coaters, multi-head coaters, roll coaters, roll/blade coaters, cast coaters, laboratory coaters, gravure coaters, kiss coaters, liquid application systems, reverse roll coaters and extrusion coaters.

Embodiments of the present invention will now be described by way of example with reference to the following illustrative Examples.

EXAMPLE 1

Example 1 shows that pigment products made from viscous crude clay according to the teachings of the invention are different from those of conventional, non-viscous clay because of their unique chemical composition as well as their poor fluidity at high solids concentration.

Both viscous crude and non-viscous crude clays from a coarse clay mine in Washington County, Georgia, were beneficiated in a typical process scheme for a standard No.2 coating clay under the same processing conditions. The products had practically the same particle size distribution: about 81% particles less than 2 microns and about 20% particles less than 0.25 microns. Table 2 shows their differences in chemical compositions and viscosities:

TABLE 2

Oxide (wt%)	No.2 Coating Clay From Non-Viscous Crude Clay	No. 2 Coating Clay From Viscous Crude Clay
SiO ₂	45.39	45.31
Al ₂ O ₃	38.87	38.80
TiO ₂	2.028	1.694
Fe ₂ O ₃	0.208	0.588
MgO	0.024	0.053
CaO	0.026	0.072
Na ₂ O	0.059	0.079
K ₂ O	0.018	0.259
Brookfield Viscosity (#2 spindle @ 20rpm)	260 c.p.s.	2000 c.p.s.
Hercules Viscosity (rpm at 18 dynes)	1310 rpm	180 rpm
Slurry Solids	70%	68.7%

The No. 2 coating clay made from viscous crude has characteristically higher concentrations of potassium and magnesium, indicating the presence of micaceous and smectitic phyllosilicates. Its viscosity is too poor as a No. 2 coating clay, which generally requires a shippable slurry of minimum 70% solids.

For Examples 2, 3 and 4 described below, the coating composition used is that for a rotogravure type of printing method of coating paper in the ULWC grade.

The composition used for Examples 2, 3 and 4 is shown in Table 3:

TABLE 3

Ingredient	Parts By Weight
Pigment Under Test	100
Synthetic Latex Binder	6
Lubricant	1
Dispersant	0.1
Thickener	0.2
Adjusted pH With Caustic	8.5

The synthetic latex binder was a styrene butadiene rubber binder of the type, which has been found to be suitable for use in rotogravure coating formulations. The parts by weight shown are parts by weight of latex solids.

The lubricant was a calcium stearate of the type which is commonly used in paper coating colors.

The dispersant was a sodium polyacrylate marketed under the trade name "C-211" and available from Rhone-Poulenc.

The thickener was an alkali swellable acrylic emulsion containing hydrophobic groups of a type which is found to be suitable for use in rotogravure coating formulations.

One side of a base sheet was coated. The coated paper was calendered as described herein above.

Each composition was coated onto base paper of substance weight 35 g.m^{-2} by means of a coating machine of the type described in GB-A-1032536 fitted with a pond head. The paper speed was 800 m.min^{-1} . Samples of a coated paper were prepared at different coat weights in the range of from about 3 g.m^{-2} to about 10 g.m^{-2} . The coated paper was dried and then subjected to calendering by passage three times between the rolls of a supercalender at a temperature of 150°F and a pressure of 200 psi.

The samples of calendered coated paper prepared from each of the coating compositions were then tested for sheet gloss; sheet brightness; opacity; Parker Print Surf (PPS) porosity using Parker Print Surf Instrument; Parker Print Surf (PPS) roughness using the soft backing material and a pressure of 1000kPa; and the missing dot test (known to those skilled in the art).

EXAMPLE 2

Example 2 demonstrates the use of naturally platy crude to make pigments of the invention, and the application of the pigments in a coating composition for rotogravure printing. This Example 2 shows that the products of the invention, the delaminated products made from viscous crude kaolin with preferred amounts

of non-kaolin phyllosilicates, yield unexpectedly superior glossing characteristics relative to conventional delaminated products.

Five pigments were made from five different viscous, Georgia sedimentary crudes A through E. Crudes A, B, C and D are coarse crudes (<80% <2 microns) whereas crude E is a fine crude (>90% <2 microns). The crudes were blunged, degritt, magnet, ground, classified, leached, filtered and dewatered. The final pigments were assayed by XRF to have chemistries shown in Table 4.

TABLE 4

Sample	Pigment A	Pigment B	Pigment C	Pigment D	Pigment E
SiO ₂	44.2780	45.6510	45.3290	44.7290	44.9460
Al ₂ O ₃	38.3080	39.4060	39.2640	38.6530	38.1600
TiO ₂	1.0540	1.0350	1.1050	0.9160	0.9930
Fe ₂ O ₃	0.3560	0.3470	0.5710	0.4420	1.0300
MgO	0.0814	0.1052	0.0464	0.0548	0.0524
CaO	0.6514	0.5111	0.0336	0.0502	0.0370
Na ₂ O	0.1542	0.1636	0.1092	0.1419	0.1520
K ₂ O	0.1677	0.1788	0.1725	0.1814	0.3815

The pigments were made down into coating colors with 15 parts No.2 coating clay and ran against 2 control pigments. One control pigment was delaminated clay with 15 parts No.2 coating clay. The second

control was delaminated clay with 12 parts No.2 coating clay and 3 parts plastic pigment. Plastic pigment is an expensive pigment additive that is used to enhance paper sheet gloss. Coating results are shown in Table 5.

TABLE 5

Description	75 Delami- nated	75 Delami- nated	75 Pigment A	75 Pigment B	75 Pigment C	75 Pigment D	75 Pigment E
	15 No. 2 Coating Clay	12 No. 2 Coating Clay	15 No. 2 Coating Clay	15 No. 2 Coating Clay	15 No. 2 Coating Clay	15 No. 2 Coating Clay	15 No. 2 Coating Clay
	10 Calcined	10 Calcined	10 Calcined	10 Calcined	10 Calcined	10 Calcined	10 Calcined
		3 Plastic Pigment					
Sheet (ISO) Brightness	68.64	69.67	69.02	67.79	68.53	69.00	68.56
Sheet Opacity, %	82.64	83.60	83.28	82.69	83.47	83.42	82.95
Sheet Gloss, %	49.10	54.42	56.34	54.49	54.34	54.85	50.52

In the first column of Table 5, the coating composition has 75 parts delaminated clay, 15 parts No. 2 clay, and 10 parts calcined clay, while in the second column, 3 parts of a No.2 clay have been replaced by 3 parts of plastic pigment, which adds significant cost to the composition. A comparison of results for these two compositions show that there is up to 5 units improvement in sheet gloss in the composition with plastic pigment and 1 unit improvement in sheet brightness, and one unit improvement in sheet opacity.

The pigments of the invention were also used in the coating composition of Table 3. In Table 5, it can be seen that coatings with Pigments A through D all show improvements in sheet brightness, opacity, and sheet gloss compared to the pigment of the first column and comparable results to the pigment of the second column. Tables 4 and 5 demonstrate that the pigments

of the invention, which have significantly different chemical composition as compared to a commercial delaminated clay, show significantly improved performance in coating application using the rotogravure printing method.

EXAMPLE 3

Example 3 shows that the products of the invention, the delaminated products made from viscous crude clay can eliminate expensive pigment components (such as plastic pigment or equivalent).

Three pigment products produced from 100% viscous, Georgia sedimentary kaolin feed were ran in coating formulations against a standard paper coating formulation containing standard delaminated kaolin, a No.2 coating kaolin, and 3 parts plastic pigment to enhance sheet gloss. The paper coated with pigments made from the viscous crude, in accordance with the teachings of the invention, performed equally to or better than the paper coated with the standard clays and the expensive plastic pigments.

The crude in this Example 3 were selected from coarse (<80% <2 microns) sedimentary kaolin strata located in Middle Georgia. The crude assays determined by XRF are shown in Table 6. Crude F had a starting mica content of about 3 wt.% and a starting smectite

content of about 2 wt.%, based on the dry weight of the kaolin crude. Crude G had a starting mica content of about 5 wt.% and a starting smectite content of about 3 wt.%, based on the dry weight of the kaolin crude.

TABLE 6

Sample	Crude F	Crude G
SiO ₂	44.6480	44.367
Al ₂ O ₃	38.3750	38.317
TiO ₂	1.3140	1.470
Fe ₂ O ₃	0.8500	0.534
MgO	0.0556	0.0862
CaO	0.0329	0.0518
Na ₂ O	0.0408	0.0675
K ₂ O	0.3501	0.6167

The crude was blunged, degrittied to remove >45 micron particles, passed through a magnetic separator and then ground in an attrition grinder. The ground products were classified to 90 wt.% <2 microns using a Bird classifier, and the clay was leached, filtered and dewatered to about 61% to 65% solids. The pigment properties are shown in Table 7, and the final coated

sheet properties relative to the control are shown in Table 8.

TABLE 7

Description	Delaminat ed Clay	No. 2 Coating Clay	Pigment F	Pigment G
Brightness(GE)	88.3	86.4	88.5	88.1
% <2 micron	84	83	92	90
% <0.25 micron	23	37	36	31
Solids %	67	70	63	62

TABLE 8

Description	75 Delam/12 #2 Coating Clay	Pigment F	Pigment G
	10 Calcined Clay	10 Calcined Clay	10 Calcined Clay
	Plastic Pigment		
TAPPI Br Brightness, ISO	68.22	67.34	67.19

TAPPI Opacity, %	83.83	83.79	84.02
Sheet Gloss 75_, %	53.79	54.56	51.71
Sheet Gloss 20_, %	7.22	8.10	7.62

The coating composition in the first column of Table 8 has 75 parts delaminated clay, 12 parts No.2 clay, 10 parts of calcined clay and 3 parts latic pigment. In the other two coating compositions, the 12 parts No. 2 clay and 3 parts of plastic pigment have been replaced by the pigments of the invention. The results show that the pigments of the invention successfully replace the expensive plastic pigment by showing equivalent opacity and sheet gloss, especially the low angle (20_) sheet gloss, which is a good indicator of micro-smoothness of the coated surface.

EXAMPLE 4

Example 4 shows that the viscous crude may be used as a major blend component along with other raw material component(s) in making the products of the invention. Example 4 further demonstrates the pigment produced according to the teachings of the invention and its use in a coating composition for use in rotogravure printing.

The pigment was made from a viscous Georgia sedimentary kaolin crude. The product was made such that 80% degrittied crude was blended with 20% coarse product obtained from a Bird centrifuge. The degrittied, viscous crude contained 0.15 wt.% of MgO (4.5% smectite component) and 1.4 wt.% of K₂O (12% mica component), based on the dry weight of the kaolin; whereas the coarse product from the Bird centrifuge contained 0.04 wt.% of MgO (1.2 wt.% smectite component) and 0.2 wt.% of K₂O (1.7 wt.% mica component). The 80/20 blend was scalped in a Bird centrifuge to remove the majority of oversized particles >45 microns to 0.07 wt.% of MgO (2.1 wt.% smectite component) and 0.28 wt.% of K₂O (2.4 wt.% mica component). The material was then passed through a magnet to remove iron impurities and then ground in an attrition grinder. The ground product was classified through a Bird centrifuge to about 88% <2 microns, leached, filtered and dewatered to 63% solids. The <0.25 micron content of the product was 29%, and BET (by Nitrogen) surface was 16.8 m²/g.

The final product MgO content was 0.06 wt.% (1.8 wt.% of smectite component) and 0.22 wt.% of K₂O (1.9 wt.% of mica component).

Paper coating results using a formulation and control similar to that describe for Example 4 are shown in Table 9.

TABLE 9

	75 Delam/12 #2 Coating Clay	Pigment H
	10 Calcined Clay	10 Calcined Clay
	Plastic Pigment	
Sheet Brightness, ISO	67.37	66.83
Opacity, %	83.15	82.91
Sheet Gloss 75_, %	49.51	54.07
Sheet Gloss 20_, %	6.72	7.80

The coating composition, shown in the first column of Table 9 comprised, 75 parts delaminated clay, 12 parts No. 2 clay, 10 parts calcined clay and 3 parts plastic pigment. The coating composition in the second column comprised 90 parts Pigment H and 10 parts calcined clay. Pigment H, made from the teachings of the invention, shows equivalent sheet brightness, and opacity. The coating composition with pigment H also shows significantly higher, such as up to 5 units, sheet gloss at the 75_ angle of gloss measurement. At the 20_ angle of gloss measurement, there is over a one

unit improvement, which signifies substantial improvement in the micro-smoothness of the paper coated with the composition made from pigment H.

Having thus described the invention, numerous changes and modifications hereof will be readily apparent to those having ordinary skill in the art, without departing from the spirit or scope of the invention.

WHAT IS CLAIMED IS

1. A pigment product suitable for a paper coating composition, the pigment comprising kaolin of a sedimentary crude having a phyllosilicate assemblage of minerals that yield a final pigment MgO content ranging from about 0.04% to about 0.3%, by weight, and a final pigment K₂O content ranging from about 0.12% to about 0.8%, by weight, based on the dry weight of the pigment.
2. A pigment product according to claim 1 wherein the MgO content ranges from about 0.05% to about 0.2%, by weight, and the K₂O content ranges from about 0.14% to about 0.9%, by weight on a dry weight basis of the pigment.
3. A pigment product according to claim 1 wherein the MgO content ranges from about 0.06% to about 0.1%, by weight and the K₂O content ranges from about 0.15% to about 0.25%, by weight on a dry weight basis of the pigment.
4. A pigment product according to claim 1 wherein the MgO content ranges from about 0.05% to about 0.2%, by weight on a dry weight basis of the pigment.

5. A pigment product according to claim 1 wherein the MgO content ranges from about 0.05% to about 0.1%, by weight on a dry weight basis of the pigment.

6. A pigment product according to claim 1 wherein the K₂O content ranges from about 0.14% to about 0.3%, by weight on a dry weight basis of the pigment.

7. A pigment product according to claim 1 wherein the K₂O content ranges from about 0.3% to about 0.5%, by weight on a dry weight basis of the pigment.

8. A pigment product according to claim 1 wherein the pigment product comprises about 1.2% to about 9.1%, by weight smectitic clays on a dry weight basis of the pigment.

9. A pigment product according to claim 1 wherein the pigment product comprises about 1.0% to about 6.7%, by weight micaceous clays on a dry weight basis of the pigment.

10. A pigment product according to claim 1 wherein the pigment product comprises about 1.5% to about 6% smectitic clays on a dry weight basis of the pigment.

11. A pigment product according to claim 1 wherein the pigment product comprises about 1.2% to about 3.4%, by weight micaceous clays on a dry weight basis of the pigment.

12. A pigment product according to claim 1 wherein the pigment product comprises about 1.8% to about 3.0% by weight smectitic clays on a dry weight basis of the pigment.

13. A pigment product according to claim 1 wherein the pigment product comprises about 1.3% to about 2.1% by weight micaceous clays on a dry weight basis of the pigment.

14. A pigment product according to claim 1 wherein the pigment product is produced from a viscous sedimentary kaolin.

15. A pigment product according to claim 1 wherein the pigment product is produced from a viscous Georgia-South Carolina sedimentary kaolin.

16. A pigment product according to claim 1 wherein the pigment product has a shape factor greater than 60.

17. A pigment product according to claim 1 wherein the pigment product has a particle size distribution such that greater than 80% by weight of the kaolin particles have an esd (equivalent spherical diameter) of less than 2 microns and greater than 12% by weight of the particles have an esd of less than 0.25 microns.

18. A pigment product according to claim 1 wherein the pigment product is processed from a kaolin of a sedimentary crude having a shape factor greater than 15.

19. A pigment product according to claim 1 wherein the pigment product has a shape factor greater than 35.

20. A pigment product according to claim 1 wherein the product has particles with a surface area greater than $12\text{m}^2/\text{g}$ when measured by the BET method.

21. A pigment product according to claim 1 wherein the product has particles with a surface area of from $15\text{m}^2/\text{g}$ to $20\text{m}^2/\text{g}$ when measured by the BET method.

22. A coating composition for use in producing gloss coatings on paper and other substrates, which composition comprises an aqueous suspension of a particulate pigment together with a hydrophilic

adhesive, wherein the particulate pigment comprises a pigment product according to claim 1.

23. A composition according to claim 22 wherein the pigment product has a viscous clay content of from about 70% to about 100% based on the dry weight of the pigment product.

24. A method comprising applying the coating composition of claim 22 to coat a sheet of paper and calendering the paper to form a gloss coating thereon.

25. A method of producing a pigment product suitable for use in a paper coating composition comprising:

providing a kaolin of a sedimentary crude having a phyllosilicate assemblage of minerals; and

forming a pigment having a MgO content ranging from about 0.04% to about 0.3% by weight, and a K₂O content ranging from about 0.12% to about 0.8% by weight, based on the dry weight of the pigment.

26. A method according to claim 25 wherein forming the pigment comprises:

mixing the sedimentary kaolin crude, comprising at least about 0.9% by weight mica and about 0.9% by weight smectite, based on the dry weight of the crude, where the K₂O content ranges from about 0.10% by weight

to about 3.0% by weight and the MgO content ranges from about 0.03% by weight to about 0.50% by weight, based on the dry weight of the kaolin crude, with water to form an aqueous suspension containing from 20% to 70% of kaolin on a dry weight basis;

attrition grinding the aqueous suspension using a particulate grinding medium for a time sufficient to delaminate the majority of stock of kaolin crude with a shape factor from about 35 to greater than 60;

separating the suspension of ground kaolin clay from the particulate grinding medium;

classifying the particles in the aqueous suspension by size; and

dewatering the aqueous suspension of ground kaolin clay to recover a pigment product.

27. A product produced according to claim 26.

28. A product produced according to claim 27, said pigment product comprising from about 1.0% to about 6.7% by weight mica and about 1.2% to about 9.1% by weight smectite based on the dry weight of the kaolin clay in the pigment product, wherein the K₂O content of the pigment product ranges from about 0.12% by weight to about 0.8% by weight and the MgO content of the pigment product ranges from about 0.04% by weight and about 0.3% by weight, based on the dry weight of the

kaolin clay in the pigment product, and the particle size distribution of the final pigment product is such that about 80% to 95% by weight of the particles have an esd less than 2 microns.

29. A pigment product according to claim 26 wherein the sedimentary kaolin crude has a MgO content of from about 0.03% to about 0.50% by weight and a K₂O content from about 0.1% to about 3.0% by weight, based on the dry weight of the kaolin crude.

30. A pigment product according to claim 26 wherein the sedimentary kaolin crude has a MgO content of from about 0.04% to about 0.25% by weight and a K₂O content from about 0.2% to about 2.0% by weight, based on the dry weight of the kaolin crude.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/08485

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : C04B 14/04, 14/10; C09C 1/02, 1/42

US CL : 106/416, 417, 468, 486; 162/181.8

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 106/416, 417, 468, 486; 162/181.8

IPC (7): C04B 14/10; C09C 1/02, 1/42

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
noneElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
none**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A, P	US 5,948,156 A (COUTELLE ET AL.) 07 September 1999 (07/09/99), see entire document.	1-30
A	US 5,332,493 A (GINN ET AL.) 26 July 1994 (26/07/94), see entire document.	1-30
Y	US 5,707,912 A (LOWE ET AL.) 13 January 1998 (13/01/98), see entire document.	1-30

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Z" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

14 JUNE 2000

Date of mailing of the international search report

07 JUL 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MICHAEL MARCHESCHI

Telephone No. (703) 308-0661

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.